

lar request, and the whole of them weighed as follows :

			oz.	d.	gr.
Gold	-	-	6	2	17
Lead	-	-	3	6	28
Pure silver	-	-	3	3	22
Bismuth	-	-	3	0	3
Copper-red	-	-	2	7	56
Iron	-	-	2	5	10
Tin	-	-	2	3	48
Antimony melted, and which had small cavities on its surface			2	1	34
Fine	-	-	2	1	2
Emery	-	-	1	2	24½
White marble	-	-	1	0	25
Pure clay	-	-	0	7	24
Marble common of Montbard			0	7	20
White gypsum, improperly called Alabaster	-	-	0	6	36
Calcareous white stone of the quarry of Anieres, near Dijon	-		6	6	6
Rock chrystal: it was a little too small, and had many defects. I presume that without them it would have weighed	-		0	6	22
Common glass	-	-	0	6	21
					Pure